BUILDING TRUST

PRODUCT DATA SHEET

SikaPlast®-161 SLK

PCE-BASED SUPERPLASTICIZING AND SET RETARDING CONCRETE ADMIXTURE

DESCRIPTION

SikaPlast®-161 SLK is a 3rd-generation polymer-based high-performance superplasticizer for producing soft-consistency concrete. SikaPlast®-161 SLK meets the requirements of ASTM C 494 Type D, and BS EN 934-2

USES

SikaPlast®-161 SLK is mainly suitable for the manufacture of concrete for RMC plants and site batch concrete. SikaPlast®-161 SLK is used for the following types of concrete:
- Bored piles
- Barrette foundations and diaphragm walls
- Ground and suspended slabs
- Columns and walls
- Bridges and cantilever
- Cement mortar and grout

FEATURES

SikaPlast®-161 SLK combines different modes of action. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, Sika-Plast®-161 SLK effects the following concrete properties:
- Long slump keeping and high water reduction
- High flowability (considerably reduced placing and compacting work)
- Faster evolution of early strength development
- Improved creep and shrinkage resistance characteristics
- When used at higher dosages, SikaPlast®-161 SLK can give extended working time. SikaPlast®-161 SLK contains neither chlorides nor other corrosion-inducing substances and can therefore be used without any restrictions for reinforced concrete structures.

PRODUCT INFORMATION

Packaging	1000 L (IBC)
Appearance and colour	Liquid / brownish colour
Shelf life	12 months if stored properly in original unopened packaging
Storage conditions	Stored in dry conditions, protected from direct sunlight and at a temperatures between +5 °C and +40°C
Density	1.11 kg/l (at 25°C) EN 934-2:2001 (E) D ± 0.03 if D > 1.10 D ± 0.02 if D ≤ 1.10 where D is manufacturer's stated value Test method—ISO 758
pH-Value	5.50 (at 25 °C) EN 934-2:2001 (E) Manufacturer's stated value ±1 or within manufacturer's stated range Test method—ISO 4316

TECHNICAL INFORMATION

Concreting guidance	Concrete placing: With the use of SikaPlast®-161 SLK, concrete of the highest quality is being produced; however, state-of-the-art concrete technology, such as mixing, placing, vibrating, and curing, must be respected and applied. Curing: Effective measures for concrete curing must be followed.
Specific advice	SikaPlast®-161 SLK is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix. For optimum utilization of the ultra-high-range water reducer, we recommend a minimum wet mixing time of 60 seconds. When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.

APPLICATION INFORMATION

Recommended dosage	0.7 – 2 L per 100 kg of cement
Compatibility	SikaPlast®-161 SLK may be combined with all Sikament, Sika® Aer, Sika® Pump, and Sikacrete® PP-1 products, but must be added separately to the mix and not premixed prior to its addition. SikaPlast®-161 SLK is compatible with all Portland cement types

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

Protective Measures: Avoid prolonged contact with skin. Wash off thoroughly with soap water. In case of contact with eyes or mouth, rinse immediately with clean warm water and seek medical attention without delay. Avoid contact with food stuff and utensils. Ecology/ Waste disposal: Do not dispose of into water or soil, but according to local regulations. Transportation: Non-hazardous Toxicity: Non-toxic

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product’s suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Lanka (Private) Limited
No. 58/12-B
Raja Mawatha
Ekala, Ja-Ela
Sri Lanka