

PRODUCT DATA SHEET

SikaPlast®-168 T

PCE BASED SUPERPLASTICIZING AND SET RETARDING CONCRETE ADMIXTURE

DESCRIPTION

SikaPlast®-168 T is a 3rd generation polymer based high performance superplasticizer for producing soft consistency concrete. SikaPlast®-168 T meets the requirements of ASTM C 494 Type D - G and BS EN 934 - 2

USES

SikaPlast®-168 T is mainly suitable for the manufacture of concrete for RMC plants and site batch concrete. SikaPlast®-168 T is used for the following types of concrete:

- Bored piles;
- Barrette foundations and diaphragm walls;
- Ground and suspended slabs;
- Columns and walls.
- Bridges and cantilever
- Cement mortar and grouts

FEATURES

PRODUCT INFORMATION

Composition	Modified Poly carboxylate in water
Packaging	1000 L IBC tank
Shelf life	12 months if stored properly in original unopened packaging.
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +40 °C
Appearance and colour	Liquid / brownish colour
Density	1.10 kg/l (at 25°C) EN 934-2:2001 (E) D ± 0,03 if D > 1,10 D ± 0,02 if D ≤ 1,10 where D is manufacturer's stated value Test method - ISO 758

SikaPlast®-168 T combines different modes of actions. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, SikaPlast®-168 T effects the following concrete properties:

- Long slump keeping and high water reduction;
- High flowability (considerably reduced placing and compacting work);
- Faster evolution of early strength development;
- Improved creep and shrinkage resistance characteristics;
- When used at higher dosages, SikaPlast®-168 T can give extended working time.

SikaPlast®-168 T contains neither chlorides nor other corrosion inducing substances and can therefore be used without any restrictions for reinforced concrete structures.

pH-Value	5.00 (at 25 °C) EN 934-2:2001 (E) Manufacturer's stated value ±1 or within manufacturer's stated range Test method - ISO 4316
Concreting guidance	Concrete placing: With the use of SikaPlast®-168 T , concrete of highest quality is being produced, however state of the art concrete technology, such as mixing, placing vibrating and curing must be respected and applied. Curing: Effective measures for concrete curing must be followed.
Specific advice	SikaPlast®-168 T is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix. For optimum utilization of the ultra-high range water reducer we recommend a minimum wet mixing time of 60 seconds. When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.
Recommended dosage	0.5 – 2 L per 100 kg of cement
Compatibility	SikaPlast®-168 T may be combined with all SikaPlast, Sika® Pump, Sikacrete® PP-1 products, but must be added separately to the mix and not premixed prior its addition. SikaPlast®-168 T is compatible with all Portland cement types.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Lanka (Private) Limited
No. 58/12-B
Raja Mawatha
Ekala, Ja-Ela
Sri Lanka



PRODUCT DATA SHEET
SikaPlast®-168 T
May 2024, Version 01.02
021301011000004039

SikaPlast-168T-en-LK-(05-2024)-1-2.pdf