

## PRODUCT DATA SHEET

# SikaPlast®-210 LK

### PCE BASED SUPERPLASTICIZING AND SET RETARDING CONCRETE ADMIXTURE

#### DESCRIPTION

SikaPlast®-210 LK is a 3rd generation polymer-based high-performance superplasticizer for producing soft consistency, concrete.  
SikaPlast®-210 LK meets the requirements of ASTM C 494 Type D - G and BS EN 934 - 2

#### USES

SikaPlast®-210 LK is mainly suitable for the manufacture of concrete for RMC plants and site batch concrete. SikaPlast®-210 LK is used for the following types:

of concrete:

- Bored piles;
- Barrette foundations and diaphragm walls;
- Ground and suspended slabs;
- Columns and walls.
- Bridges and cantilever
- Cement mortar and grouts

#### FEATURES

SikaPlast®-210 LK combines different modes of action. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, Sika-Plast®-210 LK affects the following concrete properties:

- Long slump keeping and high water reduction.
  - High flowability (considerably reduced placing and compacting work);
  - Faster evolution of early strength development;
  - Improved creep and shrinkage resistance characteristics;
  - When used at higher dosages, SikaPlast®-210 LK can Give extended working time.
- SikaPlast®-210 LK contains neither chlorides nor other corrosion-inducing substances and can therefore be used without any restrictions for reinforced concrete structures.

#### PRODUCT INFORMATION

Composition	Modified Poly carboxylate in water
Packaging	1000 L
Appearance and colour	Liquid / brownish colour
Shelf life	12 months if stored properly in original unopened packaging.
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +40 °C
Density	1.070–1.110 kg/l (at 20 °C)
pH-Value	4.00–6.00 (at 25 °C)

---

**Concreting guidance**

Concrete placing: With the use of SikaPlast®-210 LK , concrete of highest quality is being produced; however, state-of-the-art concrete technology, such as mixing, placing, vibrating, and curing must be respected and applied. Curing: Effective measures for concrete curing must be followed.

---

**Specific advice**

SikaPlast®-210 LK is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix.  
For optimum utilization of the ultra-high-range water reducer, we recommend a minimum wet mixing time of 60 seconds. When adding the balance of the batching water to adjust concrete consistency, this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.

---

**APPLICATION INFORMATION**

---

**Recommended dosage**

0.5 – 2 L per 100 kg of cement

---

**Compatibility**

SikaPlast®-210 LK may be combined with all Sikament, Sika® Aer, Sika® Pump, Sikacrete® PP-1 products, but must be added separately to the mix and not premixed prior to its addition. SikaPlast®-210 LK is compatible with all Portland cement types.

---

**Restrictions**

Overdosing will result in increased workability and setting time of the Concrete, however, provided that curing is effective, ultimate concrete strength and properties will not be affected. Use an appropriate concrete mixer and do not mix by hand. Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. Please contact Sika Technical Department for further assistance.

---

**BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

**LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

**Sika Lanka (Private) Limited**

No. 58/12-B  
Raja Mawatha  
Ekala, Ja-Ela  
Sri Lanka

**PRODUCT DATA SHEET**

SikaPlast®-210 LK  
March 2026, Version 01.01  
021301011000247333

**LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaPlast-210LK-en-LK-(03-2026)-1-1.pdf